

Rio Tinto Alcan Red Mud Materials

Please call for availability and current pricing - (720) 943-7676 or (855) 943-7676

Percentage by Weight (Dry basis)

Determined by Laboratory Bomb Digests

	Loss of Mass LOM	Al as Al ₂ O ₃	Fe as Fe ₂ O ₃	Si as SiO ₂	Ti as TiO ₂	Ca as CaO	Na as Na ₂ O	Al 143 or g Al ₂ O ₃	T.E.A.	Organic C as C
RM-02	8.4	13.9	30.7	6.2	22.6	11.2	3.0	1.9	5.7	0.16
RM-06 (CAL)	15.4	28.6	4.3	17.1	9.1	12.9	9.2	-	-	-
RM-07 (CAM)	18.40	26.9	4.00	15.70	8.20	16.50	8.40	0.05	12.20	0.25
RM-08 (CAN)	17.2	28.2	4.8	16.7	8.6	13.9	8.7	0.2	13.3	0.27
RM-09	10	21.5	34.1	12.6	7.9	4.3	7	1.2	8.2	0.23
RM-10	9.6	20.1	44.2	10.3	6.99	1.15	6.1	1.4	9.8	0.23