

CP Aluminum & Aluminum Alloys, Page 1 of 1

RM#	Lot	Grade	UNS	Sb	Be	Bi	Cd	Ca	Cr	Cu	Ga	Fe	Pb	Li
				Mg	Mn	Ni	P	Si	Sn	Ti	V	Zn	Zr	Al Bal.
6060	A	AA6060	A96060	---	---	0.001	0.0002	0.0005	0.005	0.013	0.014	0.22	0.002	---
				0.49	0.011	0.005	---	0.43	---	0.021	0.006	0.012	---	98.8
6060	B	AA6060	A96060	---	---	0.001	0.0002	0.002	0.015	0.021	0.009	0.3703	0.002	---
				0.49	0.051	0.011	---	0.49	---	0.016	0.011	0.033	---	98.5
6061	A	AA6061	A96061	---	---	0.002	---	---	0.15	0.18	---	0.61	---	---
				0.92	0.10	0.004	---	0.74	---	0.049	0.015	0.13	---	97.1
6061	B	AA6061	A96061	---	---	0.008	---	---	0.053	0.28	---	0.36	---	---
				0.91	0.061	0.012	---	0.74	---	0.021	0.010	0.10	---	97.4
6262	A	AA6262	A96262	0.011	0.002	0.48	0.001	0.001	0.12	0.30	0.012	0.41	0.60	---
				1.04	0.14	0.003	0.008	0.70	0.002	0.026	0.011	0.063	---	96.1
6262	B	AA6262	A96262	---	---	0.56	0.001	0.001	0.10	0.37	0.010	0.32	0.66	---
				1.01	0.14	0.004	0.008	0.76	---	0.021	0.014	0.014	---	96.0