

CP Nickel & Nickel Alloys, Page 1 of 3

RM#	Lot	Grade	UNS	Al	B	Ca	C	Cr	Co	Cu	Fe	Pb	Mg	Mn	Mo
				Nb	N	P	Si	S	Ta	Sn	Ti	W	V	Zr	Ni Bal.
Ni200	D	Nickel 200	N02200	0.029	---	---	0.07	0.001	0.005	0.002	0.07	---	0.008	0.14	0.002
				0.002	---	0.002	0.001	<0.001	---	---	0.004	---	---	---	99.7
R405	C	Alloy R-405	N04405	0.084	---	---	0.16	0.17	0.20	33.4	1.73	---	0.051	1.14	---
				---	---	0.012	0.13	0.066	---	---	0.013	---	---	---	62.7
K500	C	Alloy K-500	N05500	2.93	---	---	0.16	0.066	0.041	29.4	1.26	---	---	0.56	0.071
				---	---	0.011	0.063	0.005	---	---	0.50	---	0.002	0.021	64.9
X	D	Alloy X	N06002	0.12	0.003	---	0.066	20.9	1.58	0.13	19.2	---	---	0.21	8.86
				0.11	---	0.015	0.21	<0.001	---	---	0.034	0.52	0.023	0.004	48.1
C22	C	Alloy C-22	N06022	0.27	0.002	---	0.002	21.1	0.57	0.066	3.64	---	0.007	0.17	13.8
				0.029	---	0.009	0.034	<0.001	<0.005	---	0.005	3.31	0.18	0.002	56.7
333	D	Alloy 333	N06333	0.14	0.002	---	0.061	25.6	3.08	0.17	17.8	---	0.0005	1.92	3.05
				0.021	---	0.017	1.07	<0.001	0.013	---	0.006	3.17	0.025	0.001	44.0
600	A	Alloy 600	N06600	0.17	0.003	---	0.069	15.8	0.048	0.09	9.3	---	0.008	0.23	0.17
				0.04	---	0.008	0.09	0.001	---	---	0.30	0.05	0.033	0.002	73.7
600	D	Alloy 600	N06600	0.13	0.002	---	0.040	15.28	0.065	0.028	8.5	---	0.007	0.25	0.035
				0.035	---	0.006	0.31	<0.001	---	---	0.24	0.006	0.024	0.002	75.0
625	A	Alloy 625	N06625	0.28	0.001	---	0.028	22.2	0.05	0.014	4.8	---	0.002	0.11	9.0
				3.4	---	0.006	0.11	<0.001	0.007	0.002	0.31	0.042	0.008	---	59.5
625	B	Alloy 625	N06625	0.20	0.002	---	0.050	22.2	0.10	0.024	3.74	---	0.006	0.057	8.9
				3.60	---	0.004	0.10	<0.001	<0.005	---	0.25	0.023	0.019	<0.001	60.8
G3	C	Alloy G-3	N06985	0.21	0.0011	---	0.006	22.4	2.02	1.96	19.8	---	0.006	0.80	6.72
				0.42	---	0.013	0.68	0.001	---	---	0.010	0.68	0.06	<0.001	44.3
Wasp	C	Waspalloy	N07001	1.28	0.005	---	0.038	19.16	12.93	0.016	1.99	---	---	0.026	4.22
				0.034	---	0.003	0.046	0.001	0.012	---	3.02	0.043	0.072	0.048	57.1
Wasp	D	Waspalloy	N07001	1.26	0.006	---	0.033	19.17	12.44	0.014	0.79	---	---	0.017	4.26
				0.032	---	0.003	0.035	0.001	---	---	3.07	0.038	0.055	0.052	58.7
282	A	Alloy 282	N07208	In Process											
U500	C	Udimet 500	N07500	2.94	0.007	---	0.070	19.0	17.9	0.003	0.95	---	0.002	0.006	4.12
				0.044	---	0.002	0.020	0.001	0.013	---	3.00	0.025	---	0.006	51.8

CP Nickel & Nickel Alloys, Page 2 of 3

RM#	Lot	Grade	UNS	Al	B	Ca	C	Cr	Co	Cu	Fe	Pb	Mg	Mn	Mo
				Nb	N	P	Si	S	Ta	Sn	Ti	W	V	Zr	Ni Bal.
R26	C	Refractaloy 26	NA	0.17	0.004	---	0.047	18.3	19.1	0.14	19.9	---	---	0.11	3.32
				0.024	---	0.012	0.096	---	---	---	2.69	0.016	0.044	---	36.1
I700	C	AllVac I-700	NA	2.97	0.006	---	0.12	14.6	28.5	0.015	0.87	---	0.002	0.007	3.72
				0.034	---	<0.001	0.035	<0.001	0.010	---	2.51	0.012	0.014	0.078	46.5
718	A	Alloy 718	N07718	0.51	0.002	---	0.023	18.0	0.19	0.040	17.9	---	---	0.09	3.01
				4.95	---	0.007	0.082	<0.001	<0.005	0.005	0.90	0.029	0.039	0.004	54.1
718	B	Alloy 718	N07718	0.51	0.0036	---	0.021	17.7	0.14	0.030	18.6	---	0.001	0.063	2.89
				5.04	---	0.008	0.070	<0.001	0.008	0.005	0.95	0.024	0.023	0.004	53.9
718	D	Alloy 718	N07718	0.49	0.004	---	0.040	18.1	0.038	0.023	19.2	---	---	0.11	3.05
				5.2	---	0.009	0.09	0.001	<0.005	---	0.98	0.023	0.048	0.002	52.6
X750	D	Alloy X750	N07750	0.81	0.003	---	0.051	15.87	0.042	0.28	6.89	---	---	0.12	0.010
				0.95	---	0.005	0.28	0.001	<0.005	---	2.52	0.014	0.026	0.036	72.1
751	C	Alloy 751	N07751	1.24	0.018	---	0.066	15.3	0.001	0.022	8.38	---	---	0.059	0.095
				0.95	---	0.006	0.10	0.001	0.016	---	2.38	0.022	0.036	0.035	71.3
20Cb3	C	Alloy 20	N08020	0.009	0.002	---	0.023	18.8	0.12	3.43	40.7	---	---	0.32	2.22
				0.50	0.023	0.021	0.52	0.003	---	---	0.001	0.039	0.08	---	33.2
20Cb3	D	Alloy 20	N08020	0.012	0.002	---	0.021	19.8	0.38	3.27	39.0	---	---	0.43	2.09
				0.49	0.017	0.016	0.24	0.002	---	---	0.001	0.095	0.070	---	34.1
028	A	Alloy 028	N08028	0.086	0.001	---	0.020	27.1	0.17	0.80	34.0	(0.004)	0.005	1.62	3.47
				0.089	0.010	0.013	0.46	0.002	0.013	0.003	0.078	0.11	0.089	0.001	31.9
330	C	Alloy 330	N08330	0.017	0.005	0.001	0.059	18.7	0.18	0.17	42.4	---	---	1.53	0.29
				0.031	0.044	0.021	1.17	0.002	0.005	0.004	0.023	0.049	0.088	0.001	35.2
330	D	Alloy 330	N08330	0.009	0.005	0.001	0.059	18.5	0.071	0.15	43.6	---	---	1.52	0.20
				0.039	0.042	0.015	1.20	0.003	<0.005	0.003	0.017	0.049	0.086	0.001	34.4
800	C	Alloy 800	N08800	0.47	0.0003	---	0.078	20.0	0.046	0.41	43.3	---	---	0.80	0.12
				0.042	---	0.013	0.29	0.001	---	---	0.36	0.007	0.051	---	34.0
800H	C	Alloy 800H	N08810	0.53	0.0004	---	0.079	20.0	0.046	0.26	45.1	---	---	0.91	0.063
				0.020	---	0.012	0.42	0.001	---	---	0.56	0.009	0.045	---	32.0
825	A	Alloy 825	N08825	0.078	0.003	---	0.012	22.3	0.078	2.09	31.0	<0.005	---	0.46	3.24
				0.035	---	0.015	0.41	0.001	---	0.004	1.05	0.10	0.055	0.001	39.8

CP Nickel & Nickel Alloys, Page 3 of 3

RM#	Lot	Grade	UNS	Al	B	Ca	C	Cr	Co	Cu	Fe	Pb	Mg	Mn	Mo
				Nb	N	P	Si	S	Ta	Sn	Ti	W	V	Zr	Ni Bal.
901	D	Alloy 901	N09901	0.31	0.015	---	0.036	12.3	0.12	0.056	34.7	---	---	0.080	5.83
				0.02	0.027	0.007	0.11	0.003	<0.005	0.005	3.0	---	0.03	0.002	43.4
C276	D	Alloy C-276	N10276	0.05	0.001	---	0.005	15.3	0.13	---	6.8	---	0.006	0.57	15.7
				0.024	0.02	0.003	0.027	0.001	0.018	---	0.05	4.1	0.11	0.010	57.0
B2	C	Alloy B-2	N10665	0.21	0.001	---	0.008	0.43	0.076	0.016	1.20	---	0.004	0.18	27.6
				0.002	---	0.004	0.012	<0.001	---	---	0.008	0.047	0.007	---	70.3