

# Carbon Steels, Page 1 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
<a href="#">CPIron-A</a>	CP Iron	K00095	0.001	0.03	0.013	0.0002	0.001	0.001	0.002	<0.001	0.001	<0.005	0.001	0.001
			<0.001	<0.001	<0.001	0.001	0.02	0.001	<0.001	<0.001	<0.001	<0.005	0.001	0.002
<a href="#">CPIron-B</a>	CP Iron	K00095	<0.001	---	<0.001	<0.0001	<0.0001	0.001	<0.001	<0.001	0.20	---	0.015	<0.001
			0.25	<0.001	---	0.004	<0.001	0.001	<0.001	<0.001	---	0.001	---	---
<a href="#">CPIron-C</a>	CP Iron	K00095	0.094	<0.005	0.007	0.005	<0.0005	0.023	0.032	0.004	0.03	<0.005	0.20	0.007
			0.033	<0.001	0.004	<0.0005	0.008	0.020	0.003	<0.001	<0.005	<0.0005	<0.001	---
<a href="#">CPIron-D</a>	CP Iron	K00095	0.001	---	0.001	---	---	0.003	0.001	0.002	0.001	---	---	---
			0.005	---	---	0.003	0.10	0.001	---	---	---	---	---	---
<a href="#">CPIron-E</a>	CP Iron	K00095	0.001	---	<0.001	---	---	0.003	0.002	0.001	---	---	0.003	0.002
			0.004	0.001	---	0.002	0.007	0.001	0.001	<0.001	---	<0.0005	---	---
<a href="#">CPIron-F</a>	CP Iron	K00095	0.001	---	<0.001	---	---	0.003	0.001	0.001	---	---	0.002	0.002
			<0.001	0.002	<0.001	0.003	0.004	0.001	0.001	0.001	---	0.0005	---	---
<a href="#">A36-A</a>	A36 Steel	K02598	0.002	---	0.007	0.002	0.001	0.19	0.01	0.004	0.004	0.012	1.00	0.003
			0.007	0.001	---	0.03	0.19	0.022	0.002	<0.001	<0.005	---	0.002	---
A36-B	A36 Steel	K02598	<0.001	---	---	---	---	0.16	0.09	---	0.36	---	0.76	0.027
			0.09	<0.001	---	0.016	0.21	0.031	0.009	---	---	0.029	---	---
<a href="#">1018-A</a>	AISI 1018	G10180	0.002	---	0.011	0.002	0.001	0.19	0.14	0.007	0.23	<0.005	0.81	0.021
			0.07	0.004	0.005	0.011	0.28	0.032	0.009	0.001	<0.005	---	0.002	---
<a href="#">1018-B</a>	AISI 1018	G10180	0.001	---	0.004	0.0003	---	0.16	0.08	0.007	0.23	---	0.67	0.025
			0.10	---	---	0.008	0.24	0.032	0.009	0.001	<0.005	0.013	<0.001	---
<a href="#">1018-C</a>	AISI 1018	G10180	0.003	---	0.004	0.005	---	0.16	0.085	0.003	0.09	---	0.71	0.019
			0.051	---	---	0.014	0.22	0.013	0.010	---	---	---	---	---
1018-D	AISI 1018	G10180	0.003	---	---	---	---	0.17	0.126	---	0.23	---	0.72	0.02
			0.07	0.002	---	0.016	0.21	0.027	---	---	---	0.004	---	---
<a href="#">1020-A</a>	AISI 1020	G10200	---	<0.005	0.005	0.0002	---	0.23	0.12	0.008	0.18	---	0.56	0.025
			0.085	0.001	---	0.006	0.23	0.025	0.008	---	<0.005	0.020	---	---
<a href="#">1020-B</a>	AISI 1020	G10200	0.003	---	0.004	0.0002	---	0.22	0.15	0.007	0.19	---	0.56	0.029
			0.075	---	---	0.012	0.21	0.018	0.007	<0.001	<0.005	0.035	---	---
<a href="#">1021-C</a>	AISI 1021	G10210	0.001	---	0.008	<0.0002	---	0.15	0.068	0.002	0.32	<0.005	0.70	0.009
			0.07	0.001	---	0.020	0.26	0.035	0.019	0.001	<0.005	0.001	---	---

## Carbon Steels, Page 2 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
1022-A	AISI 1022	G10220	0.003			0.0002	0.0018	0.22	0.12		0.22	0.0025	0.89	0.019
			0.078	0.002	0.01	0.009	0.22	0.023	0.009	0.0017		0.034		98.5
1026-A	AISI 1026	G10260	0.001			0.0003	0.0011	0.27	0.157		0.3	0.0035	0.75	0.028
			0.082	0.002	0.0097	0.01	0.18	0.029	0.012	0.0008		0.03		98.5
<a href="#">1030-A</a>	AISI 1030	G10300	0.002	---	0.005	0.004	---	0.34	0.19	---	0.20	<0.005	0.77	0.019
			0.093	0.001	---	0.017	0.25	0.028	0.011	---	0.005	0.042	---	98.0
<a href="#">1030-B</a>	AISI 1030	G10300	0.003	<0.005	0.006	0.0002	---	0.32	0.16	0.007	0.25	<0.005	0.75	0.020
			0.080	0.003	---	0.014	0.26	0.026	0.010	0.001	---	0.040	---	98.0
<a href="#">1030-C</a>	AISI 1030	G10300	0.004	---	0.005	0.0003	0.002	0.33	0.11	0.006	0.18	---	0.75	0.027
			0.14	0.001	---	0.006	0.28	0.017	0.018	0.001	---	0.026	---	98.1
1030-D	AISI 1030	G10300				0.0002		0.32	0.19		0.24		0.84	0.028
			0.10			0.016	0.23	0.019	0.005			0.027		98.4
<a href="#">1040-A</a>	AISI 1040	G10400	0.002	---	0.0014	0.0003	---	0.42	0.19	0.002	0.26	<0.005	0.78	0.027
			0.093	0.002	0.011	0.022	0.23	0.024	0.011	---	0.006	0.032	---	97.9
1040-B	AISI 1040	G10400	0.004					0.41	0.07		0.25		0.73	0.03
			0.10			0.002	0.25	0.031	0.01			0.029		98.5
<a href="#">1045-A</a>	AISI 1045	G10450	0.025	---	0.004	---	---	0.49	0.11	---	0.11	---	0.83	0.020
			0.060	0.002	0.006	0.013	0.24	0.022	0.006	---	<0.005	0.004	---	98.1
<a href="#">1050-A</a>	AISI 1050	G10500	0.023	---	---	0.0002	---	0.49	0.13	0.006	0.19	---	0.77	0.031
			0.089	<0.001	0.007	0.011	0.28	0.020	---	0.002	<0.005	0.003	---	98.0
<a href="#">1080-A</a>	AISI 1080	G10800	0.004	---	0.004	<0.0002	---	0.81	0.14	0.007	0.20	---	0.75	0.022
			0.078	---	0.009	0.014	0.20	0.019	0.007	0.001	<0.005	0.003	0.001	97.7
<a href="#">1117-C</a>	AISI 1117	G11170	0.003	---	---	---	---	0.19	0.090	0.043	0.10	<0.005	1.21	0.023
			0.048	---	0.006	0.013	0.063	0.094	---	---	---	---	---	98.1
<a href="#">1144-C</a>	AISI 1144	G11440	0.0023	---	---	---	---	0.47	0.047	0.008	0.0033	0.027	1.59	0.007
			0.031	---	0.008	0.013	0.20	0.28	---	---	---	---	---	97.3
<a href="#">5Lx42-A</a>	API 5L x42	NA	0.025	---	---	<0.0002	---	0.13	0.18	0.006	0.12	---	1.01	0.05
			0.08	0.002	0.01	0.015	0.19	0.002	0.01	0.002	<0.005	0.064	---	98.1
<a href="#">1522-A</a>	AISI 1522	G15220	0.07	<0.005	0.005	0.0003	---	0.20	0.15	0.005	0.32	<0.005	1.26	0.04
			0.17	0.001	---	0.011	0.26	0.02	0.014	---	<0.005	0.075	---	97.4

## Carbon &amp; Low-Alloy Steels, Page 3 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
<a href="#">1524-A</a>	AISI 1524	G15240	0.027	---	---	0.0002	---	0.25	0.11	0.003	0.10	---	1.36	0.043
			0.068	0.001	---	0.011	0.24	0.017	0.005	0.002	<0.005	0.004	---	97.8
<a href="#">1541-A</a>	AISI 1541	G15410	0.036	---	---	0.0003	---	0.37	0.10	0.007	0.23	---	1.39	0.041
			0.079	0.003	---	0.017	0.23	0.030	0.009	0.002	<0.005	0.005	0.001	97.5
<a href="#">1552-A</a>	AISI 1552	G15520	0.001	<0.005	0.006	0.0003	---	0.51	0.09	0.009	0.28	<0.005	1.37	0.04
			0.09	0.001	0.02	0.015	0.24	0.02	0.013	0.002	<0.005	0.026	---	97.3
<a href="#">A70660-A</a>	A706/60	NA	0.002	0.005	0.005	0.0007	0.001	0.29	0.15	0.010	0.32	---	1.23	0.022
			0.12	0.004	0.010	0.017	0.25	0.03	0.012	0.001	0.006	0.031	<0.001	97.5
<a href="#">4130-D</a>	AISI 4130	G41300	0.041	<0.005	---	0.0002	---	0.33	0.94	0.008	0.20	<0.005	0.47	0.17
			0.23	0.002	0.02	0.015	0.28	0.010	0.010	0.002	<0.005	0.005	---	97.3
<a href="#">4140-A</a>	AISI 4140	G41400	0.005	---	---	0.0006	0.0003	0.41	0.96	0.009	0.24	---	0.85	0.18
			0.09	0.002	---	0.008	0.21	0.035	0.009	0.002	<0.005	0.027	---	97.0
<a href="#">4140-B</a>	AISI 4140	G41400	0.006	---	---	0.0005	0.0007	0.41	0.93	0.008	0.23	---	0.94	0.17
			0.09	0.002	---	0.013	0.25	0.034	0.011	0.003	<0.005	0.029	---	96.9
<a href="#">4140-C</a>	AISI 4140	G41400	0.035	---	---	0.0002	---	0.43	0.94	0.01	0.058	---	0.84	0.21
			0.18	0.001	---	0.005	0.28	0.013	0.009	0.003	<0.005	0.004	---	97.0
<a href="#">4140-D</a>	AISI 4140	G41400	0.028	<0.005	0.004	0.001	0.0005	0.42	0.98	0.009	0.17	<0.005	0.92	0.18
			0.080	---	0.008	0.013	0.27	0.023	0.008	0.002	<0.005	0.004	---	96.9
<a href="#">4140-E</a>	AISI 4140	G41400	0.027	<0.005	0.005	0.0003	---	0.42	1.00	0.009	0.14	---	0.95	0.18
			0.083	0.002	0.008	0.011	0.28	0.022	0.007	0.002	<0.005	0.004	0.002	96.9
<a href="#">4340-A</a>	AISI 4340	G43400	0.03	---	0.003	---	---	0.42	0.83	0.007	0.02	---	0.74	0.26
			1.8	0.002	0.006	0.014	0.26	0.005	0.005	0.005	---	0.005	---	95.6
<a href="#">4340-C</a>	AISI 4340	G43400	0.031	<0.005	0.010	0.0052	---	0.38	0.80	0.027	0.088	<0.005	0.69	0.24
			1.71	0.002	0.006	0.004	0.24	0.017	0.004	0.002	<0.005	0.002	---	95.7
<a href="#">4340-D</a>	AISI 4340	G43400	0.027	---	0.005	0.0002	---	0.40	0.82	0.026	0.11	---	0.79	0.20
			1.81	0.002	0.009	0.026	0.29	0.017	0.007	0.017	0.010	0.010	0.002	95.4
<a href="#">4340H-A</a>	AISI 4340H	H43400	0.026	---	0.004	---	---	0.39	0.80	0.010	0.22	---	0.69	0.21
			1.7	0.002	0.005	0.016	0.27	0.011	0.01	0.0013	---	0.003	---	95.6
<b>300M-A</b>	<b>AISI 4340M</b>	<b>K44220</b>	0.06			<0.001	<0.001	0.41	0.76	<0.05	0.17		0.74	0.40
			1.74	0.01	0.002	0.005	1.73	<0.001	0.004	<0.01	<0.05	0.09		97.5

## Low-Alloy Steels, Page 4 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
<a href="#">300M-C</a>	AISI 4340M	K44220	0.031	<0.005	0.009	0.0002	---	0.40	0.82	0.009	0.13	0.005	0.83	0.40
			1.75	0.003	---	0.005	1.56	0.003	0.007	0.007	0.007	0.005	0.055	---
<a href="#">4620-C</a>	AISI 4620	G46200	0.022	0.005	0.003	0.005	---	0.21	0.15	0.072	0.18	---	0.62	0.23
			1.74	0.002	---	0.006	0.30	0.014	0.010	0.001	<0.005	---	---	96.4
<a href="#">4820-A</a>	AISI 4820	G48200	0.024	<0.005	0.007	0.0002	---	0.19	0.14	0.01	0.17	<0.005	0.55	0.28
			3.5	0.002	---	0.01	0.26	0.02	0.01	0.0014	<0.005	0.002	---	94.8
<a href="#">4820-B</a>	AISI 4820	G48200	0.038	<0.005	0.005	0.0002	---	0.18	0.15	0.010	0.17	<0.005	0.57	0.20
			3.3	0.002	---	0.006	0.33	0.023	0.009	0.003	<0.005	0.001	---	95.0
<a href="#">4820-C</a>	AISI 4820	G48200	0.030	---	0.005	0.0002	0.001	0.18	0.11	0.013	0.20	<0.005	0.64	0.23
			3.5	0.002	0.007	0.009	0.32	0.016	0.013	0.002	---	---	0.002	94.8
<a href="#">5160-C</a>	AISI 5160	G51600	0.004	<0.005	0.010	0.0002	0.003	0.56	0.95	0.011	0.26	<0.005	0.93	0.042
			0.11	0.052	0.03	0.025	0.25	0.027	0.008	0.002	0.006	0.004	---	96.7
<a href="#">52100-D</a>	AISI 52100	G52986	0.004	<0.005	---	0.0001	---	1.00	1.40	0.011	0.056	---	0.35	0.019
			0.11	<0.001	0.007	0.005	0.29	0.005	0.004	0.005	<0.005	0.011	---	96.7
<a href="#">6150-A</a>	AISI 6150	G61500	0.029	---	---	---	---	0.45	0.97	0.007	0.12	---	0.73	0.065
			0.13	0.0013	---	0.019	0.30	0.01	0.005	0.002	<0.005	0.12	0.0013	97.0
<a href="#">6150-B</a>	AISI 6150	G61500	0.031	<0.005	0.007	0.0002	---	0.49	0.92	0.024	0.16	---	0.83	0.037
			0.13	0.003	---	0.013	0.29	0.016	0.009	0.004	---	0.15	---	96.9
<a href="#">6150-C</a>	AISI 6150	G61500	0.048	<0.005	---	0.0002	---	0.50	0.92	0.009	0.17	<0.005	0.75	0.04
			0.14	0.003	0.007	0.011	0.31	0.011	0.008	0.006	0.005	0.18	---	96.9
<a href="#">6150-D</a>	AISI 6150	G61500	0.032	<0.005	---	---	---	0.50	0.96	0.009	0.22	<0.005	0.85	0.043
			0.11	---	---	0.007	0.25	0.018	0.014	0.001	---	0.16	---	96.8
<a href="#">8620-A</a>	AISI 8620	G86200	0.024	---	---	---	---	0.20	0.57	0.003	0.032	<0.005	0.84	0.18
			0.51	0.001	---	0.02	0.25	0.024	0.001	0.003	<0.005	0.006	---	97.3
<a href="#">8620-B</a>	AISI 8620	G86200	0.024	<0.005	0.005	0.0002	0.001	0.21	0.45	0.009	0.20	---	0.81	0.18
			0.51	0.002	0.006	0.014	0.26	0.032	0.009	0.001	0.005	0.003	---	97.3
<a href="#">8620-C</a>	AISI 8620	G86200	0.028	<0.005	0.01	0.0001	---	0.20	0.52	0.033	0.15	<0.005	0.79	0.16
			0.44	0.002	0.008	0.007	0.23	0.018	0.01	0.0014	<0.005	0.003	---	97.4
<a href="#">8620-D</a>	AISI 8620	G86200	0.012	<0.005	0.017	0.0001	0.001	0.18	0.45	0.012	0.17	<0.005	0.72	0.17
			0.53	0.02	0.007	0.008	0.18	0.025	0.009	0.001	<0.005	0.003	---	97.5

## Low-Alloy Steels, Page 5 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
8620-E	AISI 8620	G86200	0.022	0.002	0.004	0.0002	0.0013	0.22	0.47	0.01	0.15	0.001	0.86	0.15
			0.42	0.004	0.009	0.01	0.22	0.024	0.012	0.0018	0.01	0.002	0.002	98.1
8740-A	AISI 8740	G87400	0.02	---	0.004	---	---	0.39	0.49	0.007	0.18	---	0.84	0.21
			0.41	---	0.01	0.023	0.24	0.010	0.007	---	---	0.004	---	97.2
8740-B	AISI 8740	G87400	0.036	---	---	---	---	0.40	0.51	0.012	0.23	---	0.94	0.22
			0.45	---	0.024	0.007	0.29	0.003	0.01	---	---	0.002	---	96.9
8740-C	AISI 8740	G87400	0.021	---	0.003	0.0001	---	0.41	0.49	0.007	0.095	---	0.84	0.21
			0.44	0.002	0.007	0.010	0.26	0.010	0.005	0.001	<0.005	0.003	---	97.2
8740-D	AISI 8740	G87400	0.025	---	0.004	0.0001	---	0.40	0.48	0.008	0.17	---	0.88	0.20
			0.41	0.002	0.008	0.016	0.26	0.011	0.011	0.001	<0.005	0.003	---	97.1
9310-A	AISI 9310	G93106	0.036	---	---	0.001	---	0.13	1.1	0.01	0.15	---	0.62	0.09
			3.1	0.002	---	0.01	0.26	0.002	0.007	0.001	---	0.004	---	94.5
9310-B	AISI 9310	G93106	0.018	---	---	0.0007	0.001	0.10	1.13	0.012	0.15	---	0.62	0.11
			3.10	0.002	---	0.009	0.26	0.001	---	0.002	0.006	0.004	0.002	94.5
9310-C	AISI 9310	G93106	0.008	<0.005	---	0.001	---	0.11	1.21	0.021	0.098	<0.005	0.61	0.12
			3.2	0.002	0.002	0.007	0.27	0.001	0.005	0.002	0.005	0.007	---	94.3
Mang-C	Manganal	J91129	0.025	---	---	---	---	1.03	0.30	0.010	0.055	---	12.8	0.069
			0.32	---	0.012	0.024	0.40	0.017	0.006	0.001	---	---	---	84.9
F11-C	1½Cr-½Mo	K11572	0.029	---	0.009	0.0004	---	0.16	1.19	0.009	0.19	---	0.55	0.44
			0.20	0.002	0.009	0.012	0.67	0.015	0.010	0.003	0.008	0.008	---	96.5
F22-C	2½Cr-1Mo	K21590	0.03	---	---	0.004	0.0005	0.14	2.35	0.018	0.14	<0.005	0.55	0.93
			0.11	0.004	---	0.01	0.30	0.02	0.008	0.002	0.007	0.006	---	95.4
Nit135-A	Nitalloy 135	K24065	1.06					0.414	1.58		0.19		0.60	0.34
			0.11			0.006	0.22	0.004						95.8
Nit135-C	Nitalloy 135	K24065	1.14	0.005	---	0.0004	---	0.40	1.66	0.006	0.11	<0.005	0.60	0.33
			0.14	0.0023	---	0.009	0.31	0.001	0.007	0.015	<0.005	0.009	0.007	95.3
D6A-C	Alloy D-6	K24728	0.011	---	---	0.0003	0.0005	0.46	1.09	0.007	0.079	---	0.78	0.99
			0.60	0.003	---	0.008	0.26	0.002	---	0.001	0.011	0.12	0.001	95.6
D6A-D	Alloy D-6	K24728	0.013	---	---	0.0003	0.0004	0.44	1.07	0.012	0.043	---	0.80	0.99
			0.60	0.003	---	0.008	0.25	0.002	---	0.001	0.009	0.13	0.001	95.6

# Low-Alloy Steels, Page 6 of 6

RM#	Grade	UNS	Al	Sb	As	B	Ca	C	Cr	Co	Cu	Pb	Mn	Mo
			Ni	Nb	N	P	Si	S	Sn	Ti	W	V	Zr	Fe Bal.
<a href="#">HYTUF-C</a>	HY-TUF	K32550	0.024	---	---	0.0004	---	0.25	0.31	0.025	0.15	<0.005	1.35	0.38
			1.82	0.0015	---	0.012	1.55	0.006	0.010	0.018	0.007	0.006	---	<b>94.1</b>
<a href="#">F5-A</a>	5Cr-½Mo	K41545	0.03	---	---	---	---	0.12	5.02	0.011	0.13	0.01	0.48	0.51
			0.11	0.002	---	0.012	0.41	0.01	0.01	0.003	0.007	0.02	---	<b>93.1</b>
<a href="#">F5-C</a>	5Cr-½Mo	K41545	0.01	<0.005	---	0.0003	0.002	0.13	5.9	0.030	0.87	0.005	0.38	0.70
			0.21	0.005	0.07	0.012	0.37	0.031	0.028	<0.001	0.011	0.17	---	<b>91.1</b>
<a href="#">F9-C</a>	9Cr-1Mo	K90941	0.004	---	---	0.0003	---	0.09	8.6	0.028	0.096	<0.005	0.41	0.92
			0.34	0.008	0.02	0.015	0.63	0.014	0.006	0.001	0.052	0.21	0.002	<b>88.5</b>
<a href="#">LAS1-A</a>	LAS-1	NA	0.26	---	0.005	0.001	---	0.45	1.40	0.004	0.28	---	0.96	0.46
			0.63	0.36	0.005	0.007	0.76	0.004	0.001	0.32	<0.005	0.28	0.002	<b>93.8</b>
<a href="#">LAS1-B</a>	LAS-1	NA	0.21	---	0.002	0.0002	---	0.39	1.30	0.005	0.26	---	0.95	0.42
			0.73	0.21	0.007	0.001	0.67	0.004	---	0.31	<0.005	0.26	0.003	<b>94.3</b>
<a href="#">LAS1-C</a>	LAS-1	NA	0.005	---	0.003	0.0004	---	0.44	1.22	0.006	0.24	---	0.96	0.39
			0.82	0.30	0.004	0.002	0.66	0.002	<0.001	0.23	0.006	0.37	0.003	<b>94.3</b>
<a href="#">LAS2-A</a>	LAS-2	NA	0.22	<0.005	0.005	0.001	---	0.017	1.25	---	0.41	---	1.67	0.82
			0.19	0.09	---	0.01	0.03	0.003	0.001	0.16	0.19	0.35	---	<b>94.6</b>
<a href="#">LAS2-B</a>	LAS-2	NA	0.33	<0.005	0.001	0.0004	---	0.001	1.29	0.006	0.39	<0.005	1.59	0.75
			0.17	0.09	---	---	0.012	0.005	0.001	0.16	0.26	0.39	---	<b>94.6</b>
<a href="#">LAS3-A</a>	LAS-3	NA	0.008	---	0.003	0.0005	---	0.62	4.6	0.006	0.96	---	0.013	1.45
			1.47	0.010	0.004	0.007	1.02	0.003	0.002	0.96	0.010	0.47	---	<b>88.4</b>
<a href="#">LAS3-B</a>	LAS-3	NA	0.006	---	---	---	---	0.62	4.81	0.005	0.93	---	0.005	1.48
			1.37	0.034	---	---	1.02	<0.001	0.002	1.14	0.08	0.44	---	<b>88.1</b>